

LOBADUR® PrimaSeal



Product description

Solvent based primer for parquet and hardwood floors in connection with LOBADUR® Waterborne Finish.

Alternative Low-Emission Products:

HS GlobaSeal GISCODE Ö40, WS EasyPrime GISCODE W3

Range of Use:

Strongly solvent based roller primer for recoating with LOBADUR waterbased finishes for hardwood floors of european and tropical types of wood. Please note the LOBA list of the different types of wood. When in doubt please check with the factory. The wood becomes a natural tint (color reinforcement). Reduces side-bonding effect of waterborne finishes. Impregnating, non layer building.

Features

- universally applicable
- good price-performance ratio
- blocking capability against wood-contents and contaminations
- no applicator marks

Technical Data

Article No.	11033	Application Rate	Roller application 100 – 120ml/m ² (8 - 10 m ² /l), 10 – 12ml/square foot
Package Size	5 l	Application Tool	LOBATOOL roller Universal 100
Packing	Box: 4 x 5 l Pallet: 128 x 5 l	Drying Time	Earliest possible recoating Roller application after 60-90 min. If there is a delay in drying wait until you can see that the surface is completely dry.
Solids	11 ± 1%	Intermediate Sanding	Do not intermediate sand PrimaSeal.
Viscosity DIN 4	14 ± 1s	Thinner	The primer is ready-to-use and cannot be diluted!
Storage and Transportation	Store in tightly closed original packages in a cool and dry place. Not sensitive to frost. Storable for at least 12 months. UN-Nr.: 1263 - ADR/RID-GGVS/E: class 3 F1, Package group II	Cleaning of Tools:	With PU thinner, or customary KH thinner.
GISCODE	G1		

Hazard warnings:

R 11: Highly flammable.
F Highly flammable

LOBADUR[®] PrimaSeal

Information on Use:

- Shake material well.
 - Using a roller apply plenty of material
 - Do not put material directly on the floor, use a LOBATOOOL sealing bucket
 - regard safety regulations
 - Regard climatic conditions*
 - Ventilate working area *
- *)Regard General Information on the strongly sovent based LOBADUR[®] products

Setup recommendations for parquet and hardwood floors:

1. Prepare surface and apply plenty of PrimaSeal.
2. Drying 60 – 90 minutes
3. roll LOBADUR[®] waterbased finish on to surface

Suitable finishes for recoating:

Normal wear	WS Life
Up to heavy wear	WS Viva WS Global WS EasyFinish
Up to extremely heavy wear	2K Supra ^{A.1} WS 2K Duo

The general Information on the use of Strongly Solvent Based LOBADUR[®] Products are part of this Information and must be noticed.